



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 569414-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

| | |
|---|---|
| Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft | |
| Test material: Curtain fabric | |
| Design: Haze | Received: 06-09-2013 Completed: 11-10-2013 |
| Fibre content: 60% polyester FR, 40% polyester (Manufacturer's information) | Sample no.: 569414-1 |
| Care label: (Not given) | Your ref.: Lone Henriksen |

| Test Methods | Results |
|---|---|
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 504 Colour fastness: 4 IMPROVED → |
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 734 Colour fastness: 4-5 IMPROVED → |
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 904 Colour fastness: 5-6 |
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 924 Colour fastness: 4-5 IMPROVED → |

Test Report no. A 569414-1

| Test Methods | Results |
|---|-----------------------------|
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 164 Colour fastness: 5 |
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 204 Colour fastness: 6 |
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 404 Colour fastness: 6 |
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 424 Colour fastness: 5-6 |
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 104 Colour fastness: 6-7 |
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 114 Colour fastness: 7 |

Test Report no. A 569414-1

| Test Methods | Results |
|---|-----------------------------|
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 124 Colour fastness: 5-6 |
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | 134 Colour fastness: 5-6 |

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.44 of 2013-01-14.

11 October 2013, Danish Technological Institute, Textile



Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Line Dahl Kristensen
Ph. Direct: +45 72 20 22 84
E-mail: line.dahl.kristensen@teknologisk.dk

Co-reader



**DANISH
TECHNOLOGICAL
INSTITUTE**

Test Report no. A 590675-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

| | |
|---|---|
| Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltøft | |
| Test material: Curtain fabric | |
| Design: Haze 504 | Received: 14-02-2014 Completed: 20-03-2014 |
| Fibre content: 60% polyester FR, 40% polyester (Manufacturer's information) | Sample no.: 590675-1 |
| Care label: (Not given) | Your ref.: Lone Henriksen |

| Test Methods | Results |
|---|--------------------|
| Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer | Colour fastness: 6 |

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.45 of 2013-11-11.

20 March 2014, Danish Technological Institute, Textile

Test responsible


Lea Larsen
Ph. Direct: +45 72 20 21 36
E-mail: lea.larsen@teknologisk.dk

Co-reader

HAZE 734


ISO105B02 XENOTEST 100 ore

COL. 2955 U ART. 22056

P.ESPOSTA



P.ESPOSTA



NOTE 6


VALUTAZIONE = 6

Studio n° 149 / 2015


Cliente: CLARITALIA

Analisi Luci XENO 100 ore

Parte Esposta



Parte Esposta



1

HAZE 924

NOTE 5

2

← cd. 5487 u
(VALUTAZIONE: 5)