



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

## Test Report no. A 656758-1

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Curtain fabric	
Design: Casita	Received: 13-07-2015 Completed: 13-08-2015
Fibre content: 100% Trevira CS (Manufacturer's information)	Sample no.: 656758-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	662 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	782 Colour fastness: 5
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	882 Colour fastness: 6  NOT VALID
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	822 Colour fastness: 7

**Test Report no. A 656758-1**

Test Methods	Results
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	752 Colour fastness: 7  NOT VALID
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	142 Colour fastness: 7
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	7 Colour fastness: 7  NOT VALID
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	122 Colour fastness: 7
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	222 Colour fastness: 7
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	432 Colour fastness: 7

**Test Report no. A 656758-1**

Test Methods	Results
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	462 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	672 Colour fastness: 6-7

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.46 of 2014-04-26.

13 August 2015, Danish Technological Institute, Textile



Charlotte Fischer  
Ph. Direct: +45 72 20 21 35  
E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Lea Larsen  
Ph. Direct: +45 72 20 21 36  
E-mail: lea.larsen@teknologisk.dk

Co-reader



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

## Test Report no. A 685721-2

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltøft	
Test material: Curtain fabric	
Design: Casita	Received: 23-02-2016 Completed: 17-03-2016
Fibre content: 100% Trevira CS (Manufacturer's information)	Sample no.: 685721-2
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	882 Colour fastness: 6
<b>Colour fastness to artificial light</b> DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	752 Colour fastness: 6

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.46 of 2014-04-26.

17 March 2016, Danish Technological Institute, Textile

*Charlotte Fischer*

Charlotte Fischer  
Ph. Direct: +45 72 20 21 35  
E-mail: charlotte.fischer@teknologisk.dk

Test responsible

*Lea Larsen*

Lea Larsen  
Ph. Direct: +45 72 20 21 36  
E-mail: lea.larsen@teknologisk.dk

Co-reader